

**AS/NZS 2269.0:2012**

Incorporating Amendment No. 1



Australian/New Zealand Standard

# **Plywood—Structural**

## **Part 0: Specifications**

Superseding AS/NZS 2269.0:2008.

**AS/NZS 2269.0:2012**



This Joint Australian/New Zealand Standard was prepared by Joint Technical Committee TM-008, Plywood Timber Products. It was approved on behalf of the Council of Standards Australia on 2 October 2012 and on behalf of the Council of Standards New Zealand on 5 October 2012.

This Standard was published on 24 October 2012

---

**The following are represented on Committee TM-008:**

Australian Building Codes Board

Australian Timber Importers Federation

BRANZ

Building Products Innovation Council

Engineered Wood Products Association of Australasia Engineers Australia

Scion

Timber Development Association (NSW)

Wood Processors Association

Additional Interests:

Mr Kevin Lyngcoln

---

**Keeping standards up to date**

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about joint Australian/New Zealand Standards can be found by visiting the Standards Web Shop at [www.saiglobal.com.au](http://www.saiglobal.com.au) or Standards New Zealand web site at [www.standards.co.nz](http://www.standards.co.nz) and looking up the relevant Standard in the on-line catalogue.

For more frequent listings or notification of revisions, amendments and withdrawals, Standards Australia and Standards New Zealand offer a number of update options. For information about these services, users should contact their respective national Standards organization.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Please address your comments to the Chief Executive of either Standards Australia or Standards New Zealand at the address shown on the back cover.

---

*This Standard was issued in draft form for comment as DR AS/NZS 2269.0.*

---

Australian/New Zealand Standard

---

# **Plywood—Structural**

---

## **Part 0: Specifications**

---

Originated in Australia in part as AS O85—1969.  
AS O89 first published 1973.  
AS O85—1969 and AS O89—1973 revised, amalgamated and redesignated as AS 2269—1979.  
First published in New Zealand as NZS 3614—1971.  
AS 2269—1979 and NZS 3614:1971 jointly revised and designated as AS/NZS 2269:1994.  
Third edition 2004.  
AS/NZS 2269:2004 revised and redesignated as AS/NZS 2269.0:2008.  
Second edition 2012.  
Reissued incorporating Amendment No. 1 (August 2015).

### **COPYRIGHT**

© Standards Australia Limited/Standards New Zealand

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher, unless otherwise permitted under the Copyright Act 1968 (Australia) or the Copyright Act 1994 (New Zealand).

Jointly published by SAI Global Limited under licence from Standards Australia Limited, GPO Box 476, Sydney, NSW 2001 and by Standards New Zealand, Private Bag 2439, Wellington 6140.

ISBN (Print) 978-1-77551-993-5

ISBN (PDF) 978-1-77551-994-2

## PREFACE

This Standard was prepared by the Joint Standards Australia/Standards New Zealand Committee TM-008, Plywood Timber Products, to supersede AS/NZS 2269.0:2008.

*This Standard incorporates Amendment No. 1 (August 2015). The changes required by the Amendment are indicated in the text by a marginal bar and amendment number against the clause, note, table, figure or part thereof affected.*

The objective of this Standard is to provide minimum performance requirements and specifications for the manufacture and application of structural plywood, acceptable to users, specifiers, manufacturers, and building authorities in Australia and New Zealand.

The objective of this revision is to align this Standard with the latest revision of AS 1720.1, *Timber structures, Part 1: Design methods* and AS/NZS 4063.2, *Characterization of structural timber, Part 2: Determination of characteristic values*.

Plywood manufactured to this Standard is suitable for use in permanent structures. The plywood may be of either hardwood or softwood veneers, or a combination of both. The quality of veneers is judged in the finished panel.

This edition includes the following changes:

- (a) Amendments have been made to characteristic properties listed in Table 4.1.
- (b) Two new F-grades, i.e., F4 and F5, have been included to reflect the ongoing changes in resource.
- (c) Amendments have been made to the formaldehyde emission classes with the removal of emission classes E<sub>2</sub> and E<sub>3</sub> and the inclusion of a new lower 'Super E<sub>0</sub>' emission class. This is to reflect marketplace expectations for lower formaldehyde emissions for structural plywood.

This Standard is Part 0 of the AS/NZS 2269 series, *Plywood—Structural*, which comprises the following parts:

AS/NZS

2269 Plywood—Structural

2269.0 Part 0: Specifications (this Standard)

2269.1 Part 1: Determination of structural properties—Test methods

2269.2 Part 2: Determination of structural properties—Evaluation methods

Five standard veneer qualities, A, S, B, C and D, are prescribed, as follows:

- A—a high quality appearance grade, suitable for clear finishing.
- S—an appearance grade, which permits characteristics as a decorative feature.
- B—an appearance grade suitable for high quality paint finishing.
- C—a non-appearance grade with a solid surface.
- D—a non-appearance grade with permitted open characteristics.

The surface grade of the plywood is determined by the quality of the face and back veneers.

Two methods for determining the stress grade for the plywood are described using the following bases:

- (i) Mechanical F-grading of plywood panels.
- (ii) In-grade testing of plywood panels.

Three formaldehyde emission classes, Super E<sub>0</sub>, E<sub>0</sub>, E<sub>1</sub>, are included.

For the design of structures or elements incorporating the use of plywood specified in this Standard, the structural grades will have characteristic strength and stiffness values as detailed in Table 4.1. These characteristic properties are to be assigned in accordance with the requirements of AS 1720.1, *Timber structures, Part 1: Design methods*, and NZS 3603, *Timber Structures Standard*.

This Standard covers the basic structural plywood product. Particular end uses may require additional processing, preservative treatment or surface finishing. Structural plywood that is exposed for a long term to wet or damp conditions or full weather exposure will need preservative treatment in accordance with AS/NZS1604.3, *Specification for preservative treatment, Part 3: Plywood*. Under these exposure conditions, the surface of the plywood will need adequate protection.

Notes to the text contain information and guidance. They are not an integral part of the Standard.

Statements expressed in mandatory terms in notes to figures are deemed to be requirements of this Standard.

The terms ‘normative’ and ‘informative’ have been used in this Standard to define the application of the appendix to which they apply. A ‘normative’ appendix is an integral part of a Standard, whereas an ‘informative’ appendix is only for information and guidance.

## CONTENTS

	<i>Page</i>
SECTION 1 SCOPE AND GENERAL	
1.1 SCOPE.....	5
1.2 APPLICATION .....	5
1.3 NORMATIVE REFERENCES .....	6
1.4 DEFINITIONS.....	6
1.5 GRADES OF STRUCTURAL PLYWOOD.....	6
1.6 DIMENSIONS AND SHAPE .....	7
1.7 MOISTURE CONTENT .....	8
1.8 FINISH .....	8
1.9 JOINTS IN SHEETS .....	8
1.10 IMMUNIZATION AND PRESERVATIVE TREATMENT .....	8
1.11 FORMALDEHYDE EMISSION CLASSES.....	9
1.12 BRANDING .....	9
SECTION 2 VENEER QUALITY	
2.1 GENERAL REQUIREMENTS FOR ALL VENEERS .....	11
2.2 QUALITY A VENEER .....	11
2.3 QUALITY S VENEER.....	13
2.4 QUALITY B VENEER.....	13
2.5 QUALITY C VENEER.....	14
2.6 QUALITY D VENEER .....	15
SECTION 3 MANUFACTURING REQUIREMENTS	
3.1 JOINTS IN VENEER .....	16
3.2 STRUCTURAL JOINTS IN PLYWOOD SHEETS.....	16
3.3 BONDING BETWEEN PLYS .....	17
3.4 ASSEMBLY OF PLYWOOD.....	17
SECTION 4 APPLICATION OF F-GRADES AND MECHANICAL PROPERTIES TO STRUCTURAL PLYWOOD PANELS	
4.1 GENERAL.....	21
4.2 MECHANICALLY F-GRADED STRUCTURAL PLYWOOD SHEETS .....	21
4.3 IN-GRADE TESTING.....	22
4.4 CAPACITY OF PLYWOOD .....	24
APPENDICES	
A STORAGE AND HANDLING OF STRUCTURAL PLYWOOD .....	25
B SECTION PROPERTIES, SECOND MOMENT OF AREA (MOMENT OF INERTIA) AND SECTION MODULUS FOR STRUCTURAL PLYWOOD.....	26
C METHOD FOR MECHANICALLY F-GRADING STRUCTURAL PLYWOOD PANELS .....	31
D INFORMATION TO BE SUPPLIED WITH INQUIRIES AND ORDERS .....	33
E EXAMPLE PROCEDURES FOR CONTINUOUS VALIDATION OF STRUCTURAL PROPERTIES OF PLYWOOD, BASED ON TESTING OF BENDING STIFFNESS AND STRENGTH.....	34
BIBLIOGRAPHY .....	38

## STANDARDS AUSTRALIA/STANDARDS NEW ZEALAND

---

**Australian/New Zealand Standard**  
**Plywood—Structural**


---



---

**Part 0: Specifications**


---

## SECTION 1 SCOPE AND GENERAL

**1.1 SCOPE**

This Standard specifies requirements for the manufacture, grading, finishing and branding of structural plywood. Specifications for both stress and surface grades are also provided. The Standard also specifies veneer quality, bond quality, standard lay-up construction, dimensional tolerances, joints, moisture content and characteristic strength and stiffness values for the nominated F-grades.

The following alternative methods for the determination of stress grades for structural plywood are also provided:

- (a) Mechanical F-grading of the finished sheet of plywood.
- (b) In-grade testing of finished plywood panels.

Five surface grades, based on the veneer quality of the face and back veneers, A, S, B, C and D and one bond quality, Type A bond, are prescribed.

**1.2 APPLICATION**

The specification for any grade of structural plywood shall consist of the requirements given in the following Sections:

- (a) General requirements ..... Section 1.
- (b) Requirements for veneers ..... Section 2.
- (c) Manufacturing requirements ..... Section 3.
- (d) Application of stress grades and mechanical properties ..... Section 4.

Relevant requirements are also specified in the following normative Appendices:

- (i) Section properties ..... Appendix B.
- (ii) Method for mechanically F-grading structural plywood panels ..... Appendix C.

NOTE: Further information and guidance can be found in the following informative Appendices:

- (a) For recommendations for correct storage and handling of structural plywood, see Appendix A.
- (b) For information to be supplied with inquiries and orders for structural plywood, see Appendix D.
- (c) For information relating to a procedure for continual verification of structural properties of plywood based upon testing of bending stiffness and strength, see Appendix E.



## **AS/NZS 2269.0:2012 Plywood - Structural - Part 0: Specifications**

This is a free sample only.

Purchase the full publication here:

<https://shop.standards.govt.nz/catalog/2269.0%3A2012%28AS%7CNZS%29/view>

Or contact Standards New Zealand using one of the following methods.

**Freephone:** 0800 782 632 (New Zealand)

**Phone:** +64 3 943 4259

**Email:** [enquiries@standards.govt.nz](mailto:enquiries@standards.govt.nz)